

SEDIPAN WACP 200

Waterborne white dip and flow coat Primer



Main product characteristics

- Fast drying
- Low grain rising
- High pore filling
- Isolating



Processing

General information



- Specific Gravity (g/cm³): 1,13± 0,02
- The product application on substrate must be done in an environment with not less than 12°C and not higher than 30°C. Coatings applied at lower temperatures will show chemical and mechanical properties worse than standard performances that can be normally achieved.
- The best runoff results will be achieved at 20°C and a relative humidity of 60%.
- Stir well before use!
- All external materials (i.e. fillers, tapes, sealing compounds, cleaners) must be checked for compatibility with the coating system before use.

Area of usage



- Stable
- Semi stable
- Unstable

Substrate preparation



- Wood must have the right wood moisture (12-15%).
- Always clean well the surfaces, removing all traces of dust, grease, waxes and resins.
- Perform sanding on raw wood with not less than 180 grit paper.

Application Table

Application	Dipping	Flow coating	Brushing
Working material	Stainless steel tank	Diaphragm pump	Mixed or synthetic hair
Thinning	Water		
Thinner in %	20	20	0 - 10
Working viscosity	12 sec in DIN 4 cup		
Application quantity (ml/m ²)	100 – 110		
Productivity per application (m ² /l) ¹⁾	7 – 8		
¹⁾ Productivity incl. added thinner and dripping loss			

SEDIPAN WACP 200

Waterborne white dip and flow coat Primer



Drying Table

Drying at 20 °C and RH% between 45–65: 100 ml/m ²		Drying in tunnel: 100 ml/m ²		
Dust free	10 minutes		Temperature	Time
Handling	30 minutes	Flash off	20 °C	15 minutes
Overcoat	2 – 4 hours	Laminar Air	30 °C	30 minutes
Stackable	2 hours	Cooling	20 °C	15 minutes
Sanding	2 hours	Stackable	At tunnel exit	

Cleaning



- Application tools must be cleaned with water after use.
- Coating left overs (washing waters, waters from spray booths, used coatings) must be disposed according to local regulations. Never dispose residues directly into drains.

Storage

- The shelf life is 18 months if the products are stored in an environment with temperature between 5 – 30°C.



Systems

Impregnation	Primer	Midcoat	Topcoat
SEDIPAN WACP 100	SEDIPAN WACP 200	SEDIPAN WACM 300	SEDIPAN WACT 600
SEDIPAN WACP 100	SEDIPAN WACP 200	SEDIPAN WACM 310	SEDIPAN WACT 500
	SEDIPAN WACP 200	SEDIPAN WACM 330	SEDIPAN WACT 500
	SEDIPAN WACT 200	SEDIPAN WACM 400	SEDIPAN WACT 600

The here mentioned coating systems are only an example, other systems are possible.



Additional notes

Availability

Packaging size	5, 20 and 1000l
Colours	White

VOC

- EU limit value for this product (Kat. A/d): 130 g/l (2010). This product contains maximum 110 g/l VOC (not thinned).

Where to find the MSDS



Please contact your local business partner.

The information given at present document is not claimed to be free from error or complete. The statements and recommendations are advisory only. We don't take any responsibility to supervise the application. The applicator is fully responsible for this and its quality control. We don't accept any liability to any person for any loss damage (direct or indirect) that may arise from any use of or reliance on any of the methods or information contained in the specification for any purpose. Created on 8th of June 2017. LG