

SEDIPAN SPUP-390

Solventborne transparent 2k PU-Alkyd spray Sealer



Main product characteristics

- Good filling properties
- Good sanding properties
- Perfect levelling
- High transparency
- Provides better scratch resistance



Processing

General Information



- The product application on substrate must be done in an environment with not less than 12°C and not higher than 30°C. Coatings applied at lower temperatures will show chemical and mechanical properties worse than standard performances that can be normally achieved.
- The best leveling results will be achieved at 20°C and a relative humidity of 60%.
- Stir well before use!
- All external materials (i.e. fillers, tapes, sealing compounds, cleaners) must be checked for compatibility with the coating system before use.

Area of usage



- Parquet
- Stairs
- Other Interior Constructions that should have a high scratch resistance

Substrate preparation



This product can be applied over any wooden element previously sanded with grain 180-220.

Property & Application Table

 	Appearance	low viscosity liquid
	Colour	pale yellow
	Solid content (weight ± 2%)	45 %
	VOC (weight ± 2%)	55 %
	Density (± 2%)	0,98 g/cm ³
	Viscosity in can (DIN 4, +/- 5sec)	30 sec
	Viscosity for Application (DIN 4, +/- 3sec)	18 sec
	Application	Cup gun
	Nozzle (Ø mm)	1,5 – 1,8
	Injection pressure (bar)	2 – 3
	Thinning	SEDIPAN STF-050
	Thinner in %	10 – 25
	Application quantity (g/m ²)	120 – 160
	Productivity per application (g/m ²) ¹⁾	240 – 320
	Suggest layers	from 2 to 3

¹⁾ Productivity incl. thinner and spraying loss

Mixing information

SEDIPAN SPUP-390

Solventborne transparent 2k PU-Alkyd spray Sealer



 	<ul style="list-style-type: none"> • Use Hardener SEDIPAN SH-179 • Mixing ratio Material to Hardener: 2 : 1 • Stir well after adding the hardener • Pot life after mixing 3 hours (depending on temperature)
----------	--

Drying Table		
	Drying at 20 °C and RH% between 45–65	
	Dust free	30 minutes
	Handling	60 minutes
	Drying	24 hours
	Sand ability	24 hours

Cleaning	
	<ul style="list-style-type: none"> • Application tools must be cleaned with thinner after use. • Coating left overs (washing thinner, waters from spray booths, used coatings) must be disposed according to local regulations. Never dispose residues directly into drains.

Storage	
<ul style="list-style-type: none"> • SEDIPAN SPUP-390 and its curing agent SEDIPAN SH-170 do not have an expiring date if stored in a cool environment in their original and sealed containers. After the use, close the containers. 	

Systems

This product can be applied under any SEDIPAN 2k PU-Alkyd clear topcoat previously sanded with 320 abrasive paper.

The mentioned coating systems are only an example, other systems are possible.

Additional notes

Availability	
Packaging size	25 l

Where to find the MSDS	
	Please contact your local business partner.

The information given at present document is not claimed to be free from error or complete. The statements and recommendations are advisory only. We don't take any responsibility to supervise the application. The applicator is fully responsible for this and its quality control. We don't accept any liability to any person for any loss damage (direct or indirect) that may arise from any use of or reliance on any of the methods or information contained in the specification for any purpose. Created on 7th of June 2016. KL